

TECHNICAL DATA SHEET

Centaur PP

Date of issue: 02-07-2025 / Date of update: 02-07-2025



Centaur PP – High-Performance Polypropylene Pellets for LFAM

Centaur PP is a high-performance polypropylene (PP) granulate specifically engineered for Large-Format Additive Manufacturing (LFAM). This advanced material delivers exceptional layer adhesion, resulting in Z-strength values that rival injection-molded polypropylene. With an elongation at break of nearly 650%, Centaur PP offers a unique combination of flexibility, toughness, and long-term durability.

As a slightly soft and flexible polypropylene, Centaur PP delivers superior impact resistance and reliable performance. Its heat resistance above 100 °C makes it a highly versatile material for demanding industrial and consumer applications.

With its unique combination of printability, toughness, chemical resistance, and thermal stability, Centaur PP stands out as a premium polypropylene material for LFAM 3D printing. It is the ideal choice for manufacturers seeking lightweight, impact-resistant, and highly durable components across a wide range of industries.

Key Features of Centaur PP Pellets for LFAM

- **Optimized for LFAM** – Easy-to-print polypropylene granulate designed for reliable performance in large-format 3D printing.
- **Food-Contact Compliant** – Safe for direct use in food-related applications and regulated environments.
- **Dishwasher & Microwave Safe** – Maintains integrity under heat and moisture exposure.
- **Lightweight Density (0.9 g/cc)** – Ideal for weight-sensitive designs and portable components.
- **Excellent Chemical Resistance** – Withstands exposure to a wide range of industrial substances.
- **Watertight Printing** – Delivers leak-proof results, even with single-wall prints.
- **Enhanced Wear & Fatigue Resistance** – Durable under mechanical stress and repetitive use.
- **Long-Term Reliability** – Proven performance across diverse environmental conditions.

Suitable Applications for Centaur PP Pellets for LFAM

- **Prosthetics and orthotics** – Lightweight, strong, and skin-contact safe.
- **Orthopedics** – durable and impact-resistant for medical applications.
- **Household appliances** – Heat- and wear-resistant components for daily use.
- **Food contact applications** – Compliant, dishwasher safe, and microwave resistant.
- **Lightweight & durable parts** – Ideal for industries where strength-to-weight ratio matters.

Material properties

MFR (230°C, 2.16kg)

Typical value

7.8 g/10min

Test Method

ISO 1183

Density

0,9 g/cm³

DSC

Mechanical properties

Tensile strength at yield

15,8 MPa

ASTM D638

Tensile strength at break

26,2 MPa

ASTM D638

Flexural modulus

402 MPa

ASTM D790

Elongation at yield

27%

DSC

Elongation at break

642%

ASTM D638

Impact strength (Izod Notched 23°C)

30 KJ/m²

ISO 179-1eA

Shore Hardness

50D

DSC

Thermal properties

Vicat Softening Temperature

103 °C

DSC

Melting Point

170 °C

-

Processing Recommendations for Centaur PP Pellets for LFAM

Pre-Drying: Not required

Centaur PP is a non-hygroscopic polymer and does not absorb moisture into its internal structure.



TECHNICAL DATA SHEET

Centaur PP

Date of issue: 02-07-2025 / **Date of update:** 02-07-2025



Zone 1: 200°C ±20 °C

Zone 2: 210°C ±20 °C

Zone 3: 220°C ±20 °C

Max temp: 240 °C

Die temp: 240°C ±10 °C

Typical extrusion settings may require optimization based on hardware used.

Storage and Handling Guidelines for Centaur PP Pellets for LFAM

Centaur PP is considered an inert and safe material under standard storage conditions, presenting no significant hazards. To ensure maximum quality, stability, and long-term performance, proper storage practices are recommended.

For best results:

- Store in a tightly sealed container to protect against moisture absorption.
- Keep in a dry, cool, and well-ventilated environment.
- Avoid direct exposure to sunlight or intense artificial light to preserve material integrity.

By following these guidelines, Centaur PP will maintain its reliability and print performance over time.

Product export information

HS code: 39021000

Description: Polypropylene (PP) resin in primary form

Origin: European Union

Disclaimer

The product and technical data provided in this datasheet are, to the best of FormFutura B.V.'s knowledge, accurate at the time of publication and are intended solely for reference and comparative purposes. Actual results may vary depending on printing conditions, model design, environmental factors, and other variables. The values presented are typical, non-binding, and should not be interpreted as guaranteed specifications.

All information supplied, whether in this document or otherwise, is believed to be reliable; however, it is provided on the express condition that the customer conducts its own evaluation to determine the product's suitability for any specific application. FormFutura B.V. makes no warranties, express or implied, regarding the accuracy or completeness of the information provided, the data on which it is based, or the results obtainable from the use of the product or such information. No warranty is made, whether of satisfactory quality, merchantability, fitness for a particular purpose, non-infringement of intellectual property rights, or otherwise, and none shall be implied.

